

CONVERTO EPS 30G PERIMETRO



COMPANY
WITH QUALITY
MANAGEMENT
SYSTEM
CERTIFIED



Technical Sheet - Issue 11/2023



Unstressed insulation panel with increased density and low water absorption suitable for external thermal insulation systems of the perimeter areas of skirting, made of sintered expanded polystyrene (EPS) with the addition of graphite.

DESCRIPTION

Unstressed thermal insulation panel made of sintered expanded polystyrene (EPS) with the addition of graphite, cut from a block and suitable for skirting buildings, applications against the ground and portions subject to accidental impact: ETICS certified in compliance with EAD 040083-00-0404 guidelines (formerly ETAG 004) and standard UNI EN 13499:2005, with "Certificate of Conformity" [UNI EN 13163]. The panels are characterized on an external face by a particular 3 mm deep knurling and thermal cuts useful to hold the panel.

MAIN PROPERTIES

- EASE OF INSTALLATION
- COST-EFFECTIVENESS
- IMPACT RESISTANCE
- LOW WATER ABSORPTION
- RECYCLED CONTENT

SIZE AND THICKNESS

Useful size: 100 cm x 50 cm

Available thicknesses: 4, 5, 6, 7, 8, 9, 10, 12, 14, 16, 18, 20 cm

TECHNICAL DATA	Symbol	Value	REFERENCE STANDARD
Thermal conductivity	λ_D	0.030 W/mK	EN 12667
Reaction to fire	EUROCLASS	E	EN 13501-1
Resistance to vapour diffusion	μ	20-40	EN 12086
Specific heat	C_p	1450 J/kgK	EN 10456
Compressive stress at 10% deformation	CS(10/Y)	≥ 120 kPa	EN826
Tensile strength perpendicular to the surface	TR	≥ 180 kPa	EN 1607
Dimensional stability	DS(N)	$\pm 0.2\%$	EN 1603
Water absorption due to partial immersion	W _{lp}	≤ 3 Kg/m ²	EN 16535
Shear strength	F _{tk}	≥ 20 kPa	EN 12090
Shear modulus	G _m	≥ 1000 kPa	EN 12090
Dimensional tolerances			
Length	L(2)	± 2 mm	EN 822
Width	W(2)	± 2 mm	EN 822
Thickness	T(1)	± 1 mm	EN 823
Squareness	S(2)	± 2 mm/m	EN 824
Flatness	P(3)	+ 3 mm	EN 825

CONVERTO EPS 30G PERIMETRO



Technical Sheet - Issue 11/2023

STORAGE PROCEDURE

Heat-reflecting material: do not cover the slabs with transparent materials and/or sheets during installation and storage.

NOTES

- If the slabs are exposed to UV light for a long period of time during installation, they should be protected by shading nets to prevent surface chalking (yellowing).
- If, due to prolonged exposure to UV light, surface powdering has occurred (the slabs appear yellowed), completely remove this powdery substance by sanding and brushing before applying the skim coat, in order to ensure proper and effective adhesion.

CERTIFICATIONS/CLASSIFICATIONS



IVAS Industria Vernici S.p.A. – Via Bellaria, 40 – 47030 San Mauro Pascoli (FC) – Italy
Tel. +39 0541 815811 – Fax +39 0541 815815 – www.gruppoivas.com – ivas@gruppoivas.com

This Technical Information Sheet is compiled to the best of our technical/scientific knowledge; however, it does not imply any liability on our part, as the conditions of use are outside our control. It is recommended that the product is always checked as being suitable for the specific application.