



Matt textured washable water-based paint

DESCRIPTION

Textured washable water-based paint based on vinyl resins in aqueous dispersion with special mineral fillers that normalize the surface, hiding small imperfections of the support, and give the surfaces an exceptional opacity. The product has obtained the Eurofins certification for Indoor Air Comfort as a guarantee that the product meets the low emission requirements, as well as the most relevant specifications in Europe; sign of attention to the quality of a healthy internal environment. For internal.

MAIN PROPERTIES

- Washable
- Filler - uniforming
- Very Matte
- Covering



BRILLIANCE



WASHABLE



BREATHABLE



COVERAGE

TECHNICAL DATA

Film aspect EN 13300	Very Matt (≤ 5 gloss 85°)
Thickness EN 13300	Class A, fine ($< 100 \mu\text{m}$)
Vapour permeability (class V) (EN 1062)	Class V2 - Medium
Classification (UNI 8681 / UNI 8682)	One-pack, physical drying matt vinylversatica topcoat paint dispersed in water (B4.C0.A.2.HF)
Hiding power (EN 13300)	Class 2(8 m ² /L)
Wet abrasion resistance (EN 13300 / EN 1062)	Class 2
Specific weight	1470 \pm 50 g/l
	8.3-9
Type of binder	Vinyl poured
Solid content	58 \pm 2%
Drying time	Can be overpainted after 6 hrs, completely dry after 12 hrs
Dirt grip (UNI 10792)	Very low
VOC	Cat A/a: limit 30 g/l (2010); this product contains a maximum of 1 g/l of VOCs

CHARACTERISTICS

Coverage	With the application of 2 coats: 6-8 m ² /l (64-86 sq ft/l)
Coverage per pack	(14 l): 112 m ² , approx. Coverage varies according to substrate absorption.
Overpaintable	Compatibility with other products: compatible with all water-based products
Colour range	White and Colours can be produced with the You Color tinting system
Dilution	Water; 10-15% = 100-150 ml per litre of product

APPLICATION

Suitable Substrates:

Cement-based plaster, painted plaster, lime-based plaster and paint, exposed reinforced concrete, precast concrete features and panels, gypsum and fibre cement walls and features.

Ambient Conditions:

min +5°C max +35°C max RH 80%

Preparation of the Substrate:

All substrates must be free of release agents, dry, clean and cohesive. The plasters must be sufficiently seasoned according

to the type of material and the manufacturer's instructions. On surfaces with mold or algae, first apply a coat of Sana Solux and wait at least 24 hours before proceeding.

Lime & Gypsum

Filling of all irregularities such as holes, cracks by applying IVASTUCCO fine synthetic resin-based stucco and subsequent sanding with sandpaper.

Consolidation by applying a coat of ACRILICA 100 acrylic fixative or MICRALICA micronized fixative.

Drywall

Filling of all irregularities such as holes, cracks by applying IVASTUCCO fine synthetic resin-based stucco and subsequent sanding with sandpaper.

Consolidation by applying one of ACRILICA 100 acrylic fixative or MICRALICA micronized fixative.

Plaster

Filling of all irregularities such as holes, cracks by applying IVASTUCCO fine synthetic resin-based stucco and subsequent sanding with sandpaper (indoors only).

Depending on the type of plaster, carry out any repairs or leveling with UNIFORM BIANCO/GRIGIO.

Consolidation by applying a coat of ACRILICA 100 acrylic fixative or MICRALICA micronized fixative.

N.B. In case of uneven surfaces (patched up, partially coloured, grouted, etc.) or application of dark and intense colours, it is advisable to apply a uniform base coat from the primer range, PRIME TECH, RASOFONDO 0.1-0.3 (IVAS) depending on the desired particle size

Type of Equipment:

brush, roller, airless spraying equipment

Application Procedure:

Dilute ECOTEX as indicated and mix with a low speed mixer. Apply two coats, waiting at least 6 hours between coats. For brush or roller painting, to achieve a uniform appearance, cross the direction of strokes during application.

STORAGE

Disposal and safety indications:

Dispose of in accordance with local regulations.

For information on possible hazards, refer to the safety data sheet

Packaging:

14 l - 5 l - 2.5 l - 1 l Quart, Gallon, 5 Gallons

Storage:

1 year when stored in undamaged packages at between 5 and 30°C; cannot endure frost and direct sunlight

TECHNOLOGIES/CERTIFICATION

