

# LISTELLO A MANO SAN MARCO



SOFT-PASTE, FREEZE-RESISTANT, MATT SLIPS.

## DIMENSIONAL AND PERFORMANCE PROPERTIES

DIMENSIONS: 25 x 5.5 x 2 cm

TECHNICAL CHARACTERISTICS	LISTELLO A MANO SAN MARCO
ACTIVE SOLUBLE SALTS CONTENT CATEGORY	S <sub>2</sub>
FIRE REACTION CLASS	Euroclass A <sub>1</sub>
WATER VAPOUR DIFFUSION COEFFICIENT	5/10 (tabulated value)
FREEZE/THAW RESISTANCE CATEGORY	F <sub>2</sub> – severe exposure
HAZARDOUS SUBSTANCES	None
AVERAGE COMPRESSIVE STRENGTH	N/mm <sup>2</sup> NR
ADHESION STRENGTH	N/mm <sup>2</sup> NR
WATER ABSORPTION	20-25 %
GROSS BULK VOLUME	1450-1600 kg/m <sup>3</sup>
GROSS BULK VOLUME	30 – 32 kg/m <sup>2</sup>
EQUIVALENT THERMAL CONDUCTIVITY	0.344-0.384 W/mK

## APPLICATION

When the reinforced layer has completely set (3-4 days), apply a layer of Glueflex Ultra with a 10mm notched trowel, using the double-spreading technique. In the case of slips with smooth back surface, apply Parastuck or Parastuck MF hydrophobic mortar to the top edge and right hand side of the Facciavita fair-faced brick slips and proceed with installation. The alignment should be carried out using a plumb-bob and line, in order to adjust the joint width so that the area between the gaps is clad with a full number of brick slips (5 to 10mm joint).

## PACKAGING

Packages of 1 m<sup>2</sup> = 60 pieces

**N.B.** This Technical Information Sheet is compiled to the best of our technical/scientific knowledge. Nevertheless, it is not binding and does not imply that we are responsible, as the conditions of use are outside our control. It is recommended that the product is always checked as being suitable for the specific application.